

Biomimetic Synthesis of Copper Nanoparticles Using *Tinospora Cordifolia* Plant Leaf Extract for Photo Catalytic Activity Applications

Parvathalu K (✉ parvathalu.k@gmail.com)

Government City College (A), Osmania University

Rajitha K

Government City College (A), Osmania University

Chandrashekar B

Government City College (A), Osmania University

Sathvik K

Government City College (A), Osmania University

Pranay Bhaskar. K

North Caroliana State University

Sreenivas B

Rice University-BRC

Pritam M

Michigan Technological University

Pushpalatha P

Government City College (A), Osmania University

Moses K

Busitema University

Bala Bhaskar P

Government City College (A), Osmania University

Research Article

Keywords: Green Synthesis, Copper Nanoparticles, Photo-catalysis, Methylene Blue dye, Dye Degradation

Posted Date: August 22nd, 2023

DOI: <https://doi.org/10.21203/rs.3.rs-3267520/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Additional Declarations: No competing interests reported.

Version of Record: A version of this preprint was published at Plasmonics on September 8th, 2023. See the published version at <https://doi.org/10.1007/s11468-023-02037-y>.

Biomimetic Synthesis of Copper Nanoparticles Using *Tinospora Cordifolia* Plant Leaf Extract for Photo Catalytic Activity Applications

Parvathalu.K¹, Rajitha.K¹, Chandrashekar.B¹, Sathvik.K¹, Pranay Bhaskar. K², Sreenivas.B³, Pritam.M⁴, Pushpalatha.P⁵, Moses.K⁶, Bala Bhaskar.P¹

¹Department of Physics, Government City College (A), Nayapul, Osmania University, Hyderabad, Telangana-500002, India

²Department of Materials Science and Engineering, North Caroliana State University, Raleigh, NC, 27695, USA

³Department of Chemistry and Biosciences, Rice University-BRC, Houston, TX, 77005, USA

⁴Department of Physics, Michigan Technological University, Houghton, MI, 49931, USA

⁵Department of Biotechnology, Government City College (A), Nayapul, Osmania University, Hyderabad, Telangana-500002, India

⁶Department of Chemistry, Faculty of Science and Education, Busitema University, P.O BOX 236 Tororo, Uganda

ABSTRACT

The copper nanoparticles (Cu-NPs), through a novel green synthesis method utilizing *Tinospora Cordifolia* (TC) aqueous leaf extract as a reducing and stabilizing agent, were synthesized, and investigated for their dye degradation potential. The bio-synthesis process, which is operationally simple, non-toxic, and cost-effective, involves using cupric oxide (CuO) as precursor materials. The degradation of dyes in water bodies is challenging research due to their stable nature; therefore, It is essential to develop potential catalyst materials with desirable properties to degrade dyes in water bodies. The CuNPs were characterized using X-Ray Diffraction (XRD), UV-Vis Spectrometer, Scanning Electron Microscopy (SEM), and Fourier Transformed Infrared spectrometer (FTIR). The FTIR results confirmed the presence of phytochemicals involved in the reduction, capping and stabilization of CuNPs, which was corroborated by the XRD data. The photo-catalytic activity of biosynthetic CuNPs was studied using methylene blue (MB) dye upon exposure to visible light source irradiation. The results showed that bio-synthesized CuNPs exhibited a high potential of dye degradation for the methylene blue dye in the presence of a visible light source and a dye degradation rate of 81% was achieved. The green synthesized CuNPs have proved to be a potential candidate for efficiently removing dyes from water bodies and provide a sustainable, environmentally friendly method for producing metal nanoparticles with excellent photo-catalytic properties.

Keywords: Green Synthesis, Copper Nanoparticles, Photo-catalysis, Methylene Blue dye, Dye Degradation

*Corresponding Author: parvathalu.k@gmail.com

1. INTRODUCTION:

Technological modernization and industrialization discharged a bulk number of industrial effluents and different organic dyes into the water bodies. Organic dyes have been used as a colorant in various industries, such as painting, textiles, leather, paper, cosmetics, hair dye, plastic, and pharmaceuticals, which cause harmful effects on aquatic animals and plants [1-4]. These organic dye materials can seriously threaten water bodies; they can cause serious health problems such as skin diseases, cancer, and allergic reactions in human beings [5-6]. To degrade dyes in water bodies, researchers have developed different methods to degrade dyes in water bodies, such as ion exchange, chemical oxidation, and photo catalytic degradation techniques [7-11]. However, photo-catalytic degradation using a photo-catalyst made of metal nanoparticles has been identified as a potential green approach to degrade dyes [12-13].

Metal nanomaterial with large surface area to volume are needed to degrade organic dyes in water bodies [14-15]. Metal nanoparticles (MNPs) such as CuNPs, ZnNPs, AgNPs are active potential photo-catalysts under sunlight due to their small band gap [16-19]. CuO is a p-type semiconductor having a narrow band gap of 2.0 to 2.7 eV [20]. CuNPs effectively respond to optical and photo-catalytic applications [20-22].

Biosynthesis of metal nanoparticles using plant leaf extract is considered the best green approach [23-25]. *Tinospora Cordifolia* (TC) is a well-known plant of the Indian medicinal plant system, and it is gaining more attention for its functionality in a wide spectrum of industrial applications [23]. It has already been used as a tonic for anti-cancer, anti-allergenic, and anti-diabetic patients [25-27]. This plant has the ability to protect against gastric mucosal damage and it can scavenge free radicals. It can also be used as the best capping and stabilizing agent to synthesise CuNPs, which can be used as the best photo-catalyst material to degrade dyes in water bodies.

The catalysis process plays a vital role in dye degradation and water purification. It has been estimated that the catalysis-based industries may produce commodities worth several trillion dollars annually, highlighting the importance of catalysis to our community [28-31] which clearly suggests that such catalysts are in global demand. But, chemical industries mainly use only heterogeneous catalysis for several reasons, such as simple catalyst separation, durability, and suitability for continuous operations. However, designing catalyst materials is not a straightforward process due to their complex structure and poor understanding of active centers. Therefore, a significant amount of research focuses on designing catalysts, which indicates the tremendous efforts that go into understanding the different synthesis of active, and stable catalysts [32-33]. This idea is crucial for the consistent mass production of solid catalysts [34-36]. Designing an optimal and stable catalyst is a bit challenging, and metal nanoparticles are the potential candidate to fulfil the quality and quantity of the global demand.

Hence, in continuation to our previous work on metal oxide nanoparticles [28-29], in this present study, we used single-step green synthesis approach to synthesize CuNPs using TC leaf extract. We also examined the degradation efficiency of synthesized CuNPs to degrade MB dye under the sunlight source. Further, the scope of this paper is based on the environment-friendly green synthesis of CuNP nanoparticles and their applications on water pollutants (different dyes) for understanding the environmental photocatalytic properties of so-synthesized samples.

2. MATERIALS AND METHODS

2.1 MATERIALS

Cupric oxide (Copper (II) Oxide), acetone, toluene, and methylene blue (MB) dye were procured from Sigma-Aldrich, Bangalore, India. *Tinospora Cordifolia* plant leaves were collected from medicinal garden, Hyderabad, India.

2.2 SYNTHESIS OF COPPER NANOPARTICLES (CuNPs)

Tinospora Cordifolia (TC) leaves were thoroughly washed with deionized water to remove any impurities. Afterward, the surface moisture of the leaves was dried at room temperature of 27°C, and they were grounded into a fine powder. Subsequently, 2g of TC powder was mixed with 75 ml of deionized water and stirred at 70°C for 20 minutes. The resulting TC extract was filtered using Whatman filter paper and then centrifuged for approximately 20 minutes.

To synthesize copper nanoparticles (CuNPs), 50ml of the TC leaf extract was filled in a burette and added dropwise (one drop per second) to 200 ml of CuO solution in a beaker. The solutions were prepared at a temperature of 90°C and mixed for 20 minutes at a speed of 600 rpm. The rate of adding leaf extract to the CuO solution from the burette was carefully controlled, while the resulting mixture was continuously stirred at 600 rpm. The final solution was heated on a hot plate at a temperature of 90°C until a noticeable change in the colour of the reaction mixture occurred. Finally, the solution was centrifuged at 5000 rpm for 20 minutes and the residue dried in an oven in order to collect the solid nanoparticle powder. The complete synthesis procedure of CuNPs is shown in **Fig.1**.




Fig.1.Biogenic Synthesis process of TC leaf extract mediated CuNPs

2.3 CHARACTERIZATION OF SYNTHESIZED CuNPs

The formation of Cu-metallic nanoparticles (CuNPs) was confirmed using UV-visible spectroscopy, which allowed for detecting Surface Plasmon Resonance (SPR). UV-Vis spectra were obtained using a UV JACO V-750 spectrometer, scanning the nanoparticle solution over a 200-800 nm wavelength range. This analysis identified synthesized CuNPs based on their characteristic absorption peaks.

Fourier Transform Infrared Spectroscopy (FTIR) was employed to identify the specific phytochemical groups responsible for forming these metallic nanoparticles (MNP). The samples were analyzed using an IR-Thermo Fisher Nicolet iS5 spectrometer, which recorded 400 to 4000

cm⁻¹ spectra. The FTIR analysis provided valuable insights into the functional groups and chemical bonds involved in the stabilization and capping of the CuNPs.

The surface morphology and sizes of the synthesized CuNPs were investigated using Scanning Electron Microscopy (SEM). Thin films of the nanoparticles were prepared on carbon-coated copper grids and examined using a ZEISS Merlin Compact instrument operating at an accelerated voltage of 20 kV. The SEM analysis allowed for the visualization of the nanoparticles and the determination of their size distribution, and morphology.

The crystal structure of the CuNPs was analyzed using X-Ray Diffraction (XRD) with a Bruker D8 Advance Instrument. This technique provided information about the synthesized nanoparticle's crystalline phases and crystallographic structure. The XRD patterns were obtained using Cu-K α radiation.

Overall, the combination of UV-visible spectroscopy, FTIR, SEM, and XRD measurements facilitated a comprehensive characterization of the synthesized CuNPs, including their photocatalytic, optical properties, chemical composition, morphology, and crystal structure.

2.4 PHOTOCATALYTIC ACTIVITY

The photo-catalytic activity of the synthesized Cu-metallic nanoparticles (CuNPs) was assessed in the degradation of methylene blue (MB) dye. In the photo-catalysis process, a visible light source was used as an alternative to sunlight. The reaction was initiated by adding a 5ml solution of CuNPs with density 10mg/ml and was added it to 40ml dye solution with density 15mg/ml. The mixture solution was stirred for 20minutes in the darkroom to establish the adsorption process. The samples were collected every 30minutes to see the absorption peak with the help of UV-Vis spectroscopy. The UV-Vis spectra were collected for pristine MB dye which showed

bands at 630nm and 430nm wavelengths. The solution was stirred under sunlight irradiation and 3ml of suspension was withdrawn at an interval of 30minutes up to 3 hours to observe the dye absorption peak. The absorption peaks were analyzed for different periods and the dye degradation was analyzed with UV-Vis spectrum data. The following equation was used to measure the dye degradation [37].

$$\text{Degradation (\%)} = \left(\frac{A_0 - A_t}{A_0} \right) \times 100$$

Where A_0 is the absorption at time =0 and A_t is the absorption at time =t

3. RESULTS

3.1 UV-VIS SPECTROSCOPY ANALYSIS

The formation of CuNPs was confirmed using UV-Vis spectroscopy. The location of the absorption band peak of CuNPs is characterized by factors such as surface morphology, size, reaction time, temperature, pre-cursor salt concentration, and aqueous leaf extract. Bio-phytochemicals found in plant leaf extract play a vital role in stabilizing and forming CuNPs. **Fig.2** shows the UV-Vs absorption spectrum of CuNPs from a wavelength range of 200 to 600nm. The absorption peak was observed as characteristic peak of CuNPs at wavelengths 282 and 330nm, which is possibly due to the electron transition from the valency band to the conduction band (inter-band transition) [38]. The band gap of the CuNPs was calculated from the absorption spectrum using Tauc equation[39].

$$ah\nu = D(h\nu - E_g)^n$$

Where $h\nu$ is the energy of the photon, E_g is the band gap of nanomaterial, and D is constant.

For $n=1/2$; the band gap was calculated to be 4.1 and 2.8eV which is much greater than that of bulk CuO which might be due to the size effect of the CuNPs. The band gap calculation is calculated at lower energy side [39]. The absorption peak indicates that the particles are in nano size with a narrow size distribution.




Fig.2. UV-Vis Absorption spectrum of biogenic CuNPs

3.2 FOURIER TRANSFORM INFRARED (FTIR) SPECTROSCOPY

The FTIR analysis data was carried out to understand the probable functional groups or bio-phytochemicals which are responsible for the formation of CuNPs. **Fig.3** represents the IR spectrum of CuNPs that was recorded from the range 400 to 4000 cm^{-1} . The observed peaks indicate to the identification of the surface functional groups or bio-phytochemicals which are responsible for bio-reducing and stabilizing the CuNPs. The high-intensity band at 652 cm^{-1} represents the stretching vibration of Cu-O linkage bands, which confirms the formation of pure CuNPs [40]. This indicates that biological functional groups in the *Tinospora Cordifolia* (TC) plant leaf extract have the dual role of reducer and stabilizer for the formation of pure CuNPs. These functional groups (aromatic, phenolic, amino groups, and hydroxyl) help to reduce copper

ions into copper nanoparticles, which was only possible under the effect of hydroxyl and carbonyl linkage in the plant leaf extract.




Fig. 3. FTIR spectrum of biogenic CuNPs

3.3 SCANNING ELECTRON MICROSCOPY

Scanning Electron Microscopy (SEM) was used to examine the surface morphology and structural features of the synthesized CuNPs. The observed images at different magnifications are depicted in **Fig.4**. The micrograph images of the as-synthesized CuNPs reveal an accumulation of CuNPs in the form of aggregates. The CuNPs tend to form aggregates to minimize their surface energy, possibly due to van-der Waal forces acting between CuNPs. The initial mechanism of Cu atoms that favours isotropic growth in the early stages which might be due to primarily atoms favouring relatively poor thermal energy. The lower thermal energy favours relatively forming a large number of CuNPs which might be due to having more active sites to deposited Cu-nanoparticles. When reaction time increases, Cu atoms acquire high thermal energy and deposited the CuNPs cluster to minimize surface energy. The shape of

CuNPs was observed as irregular-shaped structures with sizes ranging from 0.5 to 1.5 μm . The agglomerated clusters were formed, which might be due to the varying crystallization growth of CuNPs.




Fig.4. SEM morphology image of the CuNPs at different magnifications (a, b-2 μm ;c,d-1 μm)

3.4 X-RAY DIFFRACTION (XRD) ANALYSIS

The XRD analysis was used to study and identify the crystalline structure of CuNP materials. The XRD patterns reveal that the as-synthesized CuNPs were of crystalline structures and free of impurities. The CuNPs were identified on three high-intensity diffraction peaks $2\theta = 38.5^\circ$, 35.8° , and 47° corresponding with their crystal planes $\{200\}$, $\{002\}$, $\{202\}$ of CuNPs with the

monoclinic structure of CuNPs (**Fig.5**). The most intense peak is observed at (200), and the lattice constant was calculated using the following equation.

$$a = \lambda \left(\frac{\sqrt{h^2 + k^2 + l^2}}{2 \sin \theta} \right) A^0.$$

The crystalline size of the as-synthesized CuNP was measured using Debye-Scherr's formula ($D=0.9\lambda/\beta\cos\theta$). Here, λ is the wavelength of X-ray radiation used in the XRD, β is the full width of half maximum, and 2θ is the diffraction angle. The crystalline size of the nanoparticle was measured to be around 15.5nm. The XRD indicates several characteristic peaks of monoclinic structure for CuNPs as per standard JCPDS data card- 00-001-1117[41].




Fig.5. XRD pattern of CuNPs - JCPDS data card. 00-001-1117

3.6 MECHANISM OF BIOGENIC CuNPs

The reduction of the precursor CuO salt begins immediately after adding even a few drops of leaf extract, and the formation of CuNPs is demonstrated by the changing color of the solution. The bio-phytochemicals present in the *Tinospora cordifolia* (TC) plant leaf extracts play a vital role in reducing, capping and stabilizing CuNPs [42]. In this process, releasing H atoms during the conversion process of enol into keto bio-flavonoids reduces Cu metal ions into the formation of CuNPs. The precise mechanism of CuNPs synthesis mediated by the plant leaf extract is still not understood. It is speculated that the color of the CuNPs in the environment after 30 to 40 min can be attributed to oxidation, which is responsible for the synthesis of CuNPs. Electrostatic attractions may also help to bind metal oxide ions together to form stabilised nanoparticles and prevent CuNPs cluster formation. Despite the lack of a clear understanding of the metal nanoparticle synthesis mechanism, plant leaf extracts' play an important role in synthesizing CuNPs. The biogenic green synthesis approach is a potential pathway to synthesize metal nanoparticles due to its eco-friendly, non-toxic, and cost-effective features. The possible proposed mechanism of the formation of CuNPs is shown in **Fig.6**.




Fig.6. Schematic mechanism of formation of CuNPs

3.7 Evaluation of photo-catalytic Activity of Biogenic CuNPs

The photocatalytic activity of CuNPs in the degradation of MB dye is shown in **Fig.7**. The degradation rate of dyes depends on various factors such as irradiation time, type of light source, the concentration of dye and catalyst. The degradation of dyes was characterized by using sunlight as the light source. The band gap and high surface area to volume ratio significantly influence the dye degradation activity. The samples were collected after irradiation of light and characterized the absorption spectra at regular intervals using UV-Vis spectroscopy. It was found that the intensity of the absorption band reduced as the illumination time under light increased. The magnitude of absorption of MB dye in the presence of CuNPs is shown in **Fig.8**.




Fig.7. Absorption spectra of MB dye at different time intervals.




Fig.8. Absorption of MB dye at different time intervals

The main factors that are responsible for the degradation or decolonization of dyes are oxygen radicals, and hydroxyl, which degrades toxic contaminants in the dye. Further, the blue color of MB dye turns into a light blue color or colorless with time as the illumination time under light is

increased. The degradation efficiency for MB dye was 81% after about 2 hours of exposure to a light source in the presence of a photo-catalyst (CuNPs), as shown in **Fig.9**. It was noted that the higher the degradation rate is observed, for the faster reaction rate of dyes with a catalyst.




Fig.9. Degradation rate of MB dye

3.7.1 KINETIC STUDIES of BIOGENIC CuNPs

The photocatalytic performance of MB dye degradation kinetic behavior procedure of CuNPs catalyst examined by the first order kinetic theory model which can be expressed as

$$\ln\left(\frac{A_0}{A_t}\right) = kt \quad (1)$$

In the above equation, A_0 is the dye absorption at time $t=0$, A_t is the dye absorption at time t , and k is the rate constant. The kinetic photo-degradation of MB dye by CuNPs was investigated and results are depicted in **Fig.10** ($\frac{A_0}{A_t}$ versus time) and **Fig.11** ($\ln\left(\frac{A_0}{A_t}\right)$ versus time). Therefore, the rate constant of MB dye degradation by CuNPs measured using the first order of reaction (-

pseudo-first-order kinetics) which is attributed to the degradation of dye [43]. The slope of the fitting line determines the rate constant for the biosynthesis of CuNPs. In the presence of visible a light source, the bio-phytochemicals present in the TC extract promoted the transfer of electrons from the valency band to the conduction band of CuNPs, which increases the superoxide radicals and leads to higher efficiency of photo-degradation of CuNPs catalyst.




Fig.10. Kinetic results for dye degradation: (A_t/A_0) vs Time




Fig.11. Kinetic results for dye degradation: $\ln(A_t/A_0)$ vs Time

3.7.2 POSSIBLE MECHANISM OF BIOGENIC CuNPs





Fig.12. Schematic representation of photo-catalytic degradation of dye

The primary species involved in detoxifying dye molecules under light irradiation were identified via the photo-catalysis process. **Fig.12** represents the proposed mechanism for the photocatalytic degradation of dye. Metal nanoparticles with a small band gap promote the creation of electron-hole pairs, as low absorption energy is required for electrons to move between the highest occupied molecular orbit state to the lowest unoccupied molecular orbit state. When a catalyst (CuNPs) absorbs light energy, the absorption intensity is equal to the band gap energy of the catalyst (CuNPs). The electron transition occurs from the ground state to the excited state, creating a gap, a valence band hole (h^+), a free electron, and a conduction band e^- .

The hole is a promising candidate to accept an electron from pollutants to degrade them. Highly oxidizing species convert the water molecules into hydroxyl radicals (OH), degrading the organic contaminants. Oxygen molecules combine with an electron and convert into superoxide radicals (O_2^-) [44]. The process involved in the reduction of pollutants is given as follows.



The surface of the CuNPs was anchored by the phenols and bio-flavonoids of TC extract. These phytochemicals can enhance the oxygen to superoxide radicals, which improves the photocatalytic activity. It is observed that oxide and hydroxyl radicals are the main reactive species during photo-catalysis dye degradation of water-soluble dyes.

3.7.3 FACTORS AFFECTING PHOTOCATALYTIC DEGRADATION OF BIOGENIC CuNPs

In order to achieve potential photo-catalytic activity, some features must be considered, such as the concentration of dye, concentration of the photo-catalyst, structure and morphology of the catalyst, irradiation time, and light source. An inhibited reaction is observed when the concentration of dyes is increased, as there is no interaction with the catalyst's active sites. This is due to the dye's lack of absorption of light intensity by the dye molecules and the difficulty of electrons to migrate to the photo-catalyst, resulting in insufficient hydroxyl radicals for dye degradation, reducing the efficiency of dye degradation. We noted that MB dye solution with a 1mg/lit concentration produced better results.

As the concentration of photo-catalyst is increased, a large number of reaction sites becomes available, leading to an increased production of electron-hole pairs which helps to produce hydroxyl radicals for efficient detoxification of organic pollutants. The morphology and size of CuNPs play an important role in producing higher efficiency in dye degradation. Smaller-sized catalyst nanoparticles show higher efficiency for dye degradation as they provide more active sites for the absorption of dyes. In our studies, a good result was obtained using 10mg/ml CuNPs (95ml solution) and the dye degradation rate of 81% was achieved after a time duration of 120min. Other methods of CuNPs catalyst fabrication showed degradation efficiency varying from 32% to 95%. Our CuNPs catalyst was prepared in a simple, single-step green synthesis process using TC leaf extract and it showed dye degradation efficiency of 81% using MB under the visible light source. This value is within the reported literature using other preparation methods and extracts, but our synthesis method is much simpler, non-toxic, and eco-friendly.

4. CONCLUSION

In this study, we successfully synthesized copper nanoparticles (CuNPs) using a novel, one-step, eco-friendly, and cost-effective biogenic synthesis method. The bio-components present in *Tinospora cordifolia* (TC) leaf extract served as an excellent reducing and stabilizing agent during the synthesis process. The UV-Vis and XRD analysis confirmed the high purity and monoclinic crystal structure of the CuNPs phase with a crystalline size of 15.5nm. The green synthesized CuNPs reveal monoclinic crystal clusters with different diameters. Through the degradation of MB dye, the synthesized biogenic CuNPs effectively demonstrated photo-catalytic properties under visible light illumination. The photo-catalytic reduction followed pseudo-first-order kinetics, with a removal degradation rate of 81% for MB dye. The biosynthesized route is more important than chemically because it offers a new means for

researchers to produce cost-effective, highly active sites, high purity, non-toxic, eco-friendly and low energy consumption. It is concluded that biogenic CuNPs with TC extract are the best photo-catalyst candidate for dye degradation. Further studies should also focus on optimizing the concentrations of catalyst, and dye, clearly understanding the photo-catalyst mechanisms, evaluating potential toxicity effects, assessment of the long-term stability and performance of the CuNPs in real-world applications. These efforts will facilitate the translation of synthesis of CuNPs from the laboratory scale to large-scale industrial production, with the goal of benefiting human health and the environment.

AUTHOR'S CONTRIBUTION

Parvathalu.K: Supervision, writing-original draft and editing, visualization

Rajitha.K and Chandrasekhar.B: Designing experiment, and Data collection,

Pranay Bhaskar.K, Sathvik.K and Bala Bhaskar.P: Review of articles and data collection

All other authors were involved in various parts of discussion of the project.

DATA AVAILABILITY

Data is provided with the request.

DECLARATION

CONFLICT OF INTEREST

The authors declare no competing interest.

FUNDING

No funding was received for this project.

REFERENCES

1. Hanafi, M.F.; Sapawe, N. A review on the water problem associate with organic pollutants derived from phenol, methyl orange, and remazol brilliant blue dyes. Mater. Today Proc. **2020**, 31, 141-150.

2. Pavithra, K.G.; Jaikumar, V. Removal of colorants from wastewater: A review on sources and treatment strategies. *J. Ind. Eng.Chem.* **2019**, *75*, 1-19.
3. Ismail, M.; Akhtar, K.; Khan, M.; Kamal, T.; Khan, M.A.; M Asiri, A.; Seo, J.; Khan, S.B. Pollution, toxicity and carcinogenicity of organic dyes and their catalytic bio-remediation. *Curr. Pharm. Des.* **2019**, *25*, 36453-663.
4. Naseem K., Begum R., Wu W., Irfan A., Al-Sehemi A.G., Farooqi Z.H. Catalytic reduction of toxic dyes in the presence of silver nanoparticles impregnated core-shell composite microgels. *J. Clean. Prod.* **2019**;211:855-864.
5. Daniel S., Syed P.S. Shabudeen Sequestration of carcinogenic dye in waste water by utilizing an encapsulated activated carbon with nano MgO. *Int. J. Chemtech Res.* **2014**;7:2235-2243.
6. Vasantharaj S., Sathiyavimal S., Saravanan M., Senthilkumar P., Gnanasekaran K., Shanmugavel M., Pugazhendhi A. Synthesis of ecofriendly copper oxide nanoparticles for fabrication over textile fabrics: characterization of antibacterial activity and dye degradation potential. *J. Photochem. Photobiol. B Biol.* **2019**;191:143–149.
7. Reddy, C.V.; Reddy, K.R.; Harish, V.a.; Shim, J.; Shankar, M.; Shetti, N.P.; Aminabhavi, T.M. Metal-organic frameworks (MOFs)- based efficient heterogeneous photo-catalysts: Synthesis, properties and its applications in photocatalytic hydrogen generation, CO₂ reduction and photodegradation of organic dyes. *Int. J. Hydrog. Energy* **2020**, *45*, 7656-7679.
8. Khan, S.; Bhardwaj, U.; Iqbal, H.M.; Joshi, N. Synergistic role of bacterial consortium to biodegrade toxic dyes containing wastewater and its simultaneous reuse as an added value. *Chemosphere* **2021**, *284*, 131273.
9. Ahmad, A.; Mohd-Setapar, S.H.; Chuong, C.S.; Khatoon, A.; Wani, W.A.; Kumar, R.; Rafatullah, M. Recent advances in new generation dye removal technologies: Novel search for approaches to reprocess wastewater. *RSC Adv.* **2015**, *5*, 30801-30818
10. Adane, T.; Adugna, A.T.; Alemayehu, E. Textile industry effluent treatment techniques. *J. Chem.* **2021**, 5314404, 1-14.
11. Rao, S.; AS, S.; Jayaprakash, G.K.; Swamy, M.M.; K, S.; Kumar, D. Plant seed extract assisted, eco-synthesized C-ZnO nanoparticles: Characterization, chromium(VI) ion adsorption and kinetic studies. *Luminescence*, **2022**;
12. hmed, A.; Usman, M.; Yu, B.; Ding, X.; Peng, Q.; Shen, Y.; Cong, H. Efficient photocatalytic degradation of toxic Alizarin yellow R dye from industrial wastewater using biosynthesized Fe nanoparticle and study of factors affecting the degradation rate. *J.Photochem. Photobiol. B Biol.* **2020**, *202*, 111682.
13. Aroob, S.; Taj, M.B.; Shabbir, S.; Imran, M.; Ahmad, R.H.; Habib, S.; Raheel, A.; Akhtar, M.N.; Ashfaq, M.; Sillanpää, M. In situ biogenic synthesis of CuO nanoparticles over graphene oxide: A potential nanohybrid for water treatment. *J. Environ. Chem. Eng.***2021**, *9*, 105590.
14. Mitra, M.; Ahamed, S.T.; Ghosh, A.; Mondal, A.; Kargupta, K.; Ganguly, S.; Banerjee, D. Polyaniline/reduced grapheme oxide composite-enhanced visible-light-driven photocatalytic activity for the degradation of organic dyes. *ACS Omega* **2019**, *4*,1623-1635.
15. Feng, S.; Li, F. Photocatalytic dyes degradation on suspended and cement paste immobilized TiO₂/g-C₃N₄ under simulated solar light. *J. Environ. Chem. Eng.* **2021**, *9*, 105488.

16. Karthikeyan, C.; Arunachalam, P.; Ramachandran, K.; Al-Mayouf, A.M.; Karuppuchamy, S. Recent advances in semiconductor metal oxides with enhanced methods for solar photocatalytic applications. *J. Alloy. Compd.* **2020**, 828, 154281
17. TA, SDEM'IRC'I, T.Ç. Synthesis of copper-doped nickel oxide thin films: Structural and optical studies. *Chem. Phys. Lett.* **2020**, 738, 136884.
18. Kalakonda P. Synthesis of silver nanowires for highly conductive and transparent films. *Nanomaterials and Nanotechnology.* **2016**;6.
19. Kalakonda, P., Sreenivas, B. Synthesis and Optical Properties of Highly Stabilized Peptide-Coated Gold Nanoparticles. *Plasmonics*, **2017**, 12, 1221-1225
20. Naseem, T.; Durrani, T. The role of some important metal oxide nanoparticles for wastewater and antibacterial applications: A review. *Environ. Chem. Ecotoxicol.* **2021**, 3, 59-75.
21. Pourmoslemi, S.; Bayati, N.; Mahjub, R. Application of Box–Behnken design to optimize a sol-gel synthesis method for Ag and Zn doped CuO nanoparticles with antibacterial and photocatalytic activity. *J. Sol-Gel Sci. Technol.* **2022**, 104, 319-329
22. Elysabeth, T.; Mulia, K.; Ibadurrohman, M.; Dewi, E.L. A comparative study of CuO deposition methods on titania nanotube arrays for photoelectrocatalytic ammonia degradation and hydrogen production. *Int. J. Hydrog. Energy* **2021**, 46, 26873-26885.
23. Ahmad, S. M., et al. "Phylogenetic patterns and genetic diversity of Indian *Tinospora* species based on chloroplast sequence data and cytochrome P450 polymorphisms." *Plant systematics and evolution* 281,**2009**, 87-96.
24. Asthana, J. G., et al. "Evaluation of antileprosy herbal drug combinations and their combinations with dapsone." *INDIAN DRUGS-BOMBAY*, **2001**, 38.2 , 82-86.
25. Stanely Mainzen Prince, P., and Venugopal P. Menon. "Antioxidant action of *Tinospora cordifolia* root extract in alloxan diabetic rats." *Phytotherapy Research: An International Journal Devoted to Pharmacological and Toxicological Evaluation of Natural Product Derivatives* 15.3, **2001**, 213-218.
26. Goel, Harish Chandra, et al. "Radioprotective potential of an herbal extract of *Tinospora cordifolia*." *Journal of radiation research*, **2004**, 45.1, 61-68.
27. Prince, P. Stanely Mainzen, and Venugopal P. Menon. "Antioxidant activity of *Tinospora cordifolia* roots in experimental diabetes." *Journal of ethnopharmacology* , **1999**, 65.3, 277-281.
28. Parvathalu, K., Kumar, D.N., Rajitha, K. *et al.* Facile Synthesis of Silver Nanoparticles Using Green Tea Leaf Extract and Evolution of Antibacterial Activity. *Plasmonics* (2023), <https://doi.org/10.1007/s11468-023-01899-6>
29. Parvathalu, K., Chinmayee, S., Preethi, B. *et al.* Green Synthesis of Silver Nanoparticles Using *Argyrea nervosa* Leaf Extract and Their Antimicrobial Activity. *Plasmonics*, **2023**, **18**, 1075–1081.
30. Sharma, P., Pant, S., Poonia, P. *et al.* Green Synthesis of Colloidal Copper Nanoparticles Capped with *Tinospora cordifolia* and Its Application in Catalytic Degradation in Textile Dye: An Ecologically Sound Approach. *J Inorg Organomet Polym*, **2018**, **28**, 2463-2472.
31. Udayabhanu, P.C. Nethravathi, M.A. Pavan Kumar, D. Suresh, K. Lingaraju, H. Rajanaika, H. Nagabhushana, S.C Sharma, *Tinospora cordifolia* mediated facile green synthesis of cupric oxide nanoparticles and their photocatalytic, antioxidant and antibacterial properties, *Materials Science in Semiconductor Processing*, 2015, **33**, 81-88.

32. Kandasamy Selvam, Chinnappan Sudhakar, Muthusamy Govarthanan, Periasamy Thiyagarajan, Arumugam Sengottaiyan, Balakrishnan Senthilkumar, Thangasamy Selvakumar, Eco-friendly biosynthesis and characterization of silver nanoparticles using *Tinospora cordifolia* (Thunb.) Miers and evaluate its antibacterial, antioxidant potential, *Journal of Radiation Research and Applied Sciences*, **2017**, 10, 6-12,
33. Lumsangkul Chompunut, Tapingkae Wanaporn, Wongchai Anupong, Mathiyazhagan Narayanan, Maha Alshiekheid, Amal Sabour, Indira Karuppusamy, Nguyen Thuy Lan Chi, Rajasree Shanmuganathan, Synthesis of copper nanoparticles from the aqueous extract of *Cynodon dactylon* and evaluation of its antimicrobial and photocatalytic properties, *Food and Chemical Toxicology*, **2022**, 166, 113245,
34. Munnik, P.; De Jongh, P.E.; De Jong, K.P. Recent developments in the synthesis of supported catalysts. *Chem. Rev.* **2015**, 115, 6687–6718
35. Schüth, F. Control of solid catalysts down to the atomic scale: Where is the limit? *Angew. Chem. Int. Ed.* **2014**, 53, 8599–8604.
36. Schüth, F. Strukturierung fester Katalysatoren bis hinab zur atomaren Skala: Wo liegen die Grenzen? *Angew. Chem.* **2014**, 126, 8741–8747.
37. Lilhare, S.; Mathew, S.B.; Singh, A.K.; Carabineiro, S.A.C. Calcium Alginate Beads with Entrapped Iron Oxide Magnetic Nanoparticles Functionalized with Methionine-A Versatile Adsorbent for Arsenic Removal. *Nanomaterials* **2021**, 11, 1345.
38. Usha, V.; Kalyanaraman, S.; Thangavel, R.; Vettumperumal, R. Effect of catalysts on the synthesis of CuO nanoparticles: Structural and optical properties by sol–gel method. *Superlattices Microstruct.* **2015**, 86, 203-210.
39. A. Khorsand Zak, R. Razali, W.H.A. Majid, M. Darroudi, *Int. J. Nanomed.* **2011**, 6, 1399–1403
40. Bonnia, N.N.; Fairuzi, A.A.; Akhir, R.M.; Yahya, S.M.; Rani, M.A.A.; Ratim, S.; Rahman, N.A.; Akil, H.M. Comparison study on biosynthesis of silver nanoparticles using fresh and hot air oven dried *IMPERATA CYLINDRICA* leaf. *IOP Conf. Ser. Mater. Sci. Eng.* **2017**, 290, 012002.
41. Yadav, S.; Asthana, A.; Singh, A.K.; Chakraborty, R.; Vidya, S.S.; Susan, M.A.; Carabineiro, S.A.C. Adsorption of cationic dyes, drugs and metal from aqueous solutions using a polymer composite of magnetic/beta-cyclodextrin/activated charcoal/Nalginate: Isotherm, kinetics and regeneration studies. *J. Hazard. Mater.* **2021**, 409, 124840
42. Aroob, S.; Taj, M.B.; Shabbir, S.; Imran, M.; Ahmad, R.H.; Habib, S.; Raheel, A.; Akhtar, M.N.; Ashfaq, M.; Sillanpää, M. In situ biogenic synthesis of CuO nanoparticles over graphene oxide: A potential nanohybrid for water treatment. *J. Environ. Chem. Eng.* **2021**, 9, 105590.
43. Shreyash, N.; Bajpai, S.; Khan, M.A.; Vijay, Y.; Tiwary, S.K.; Sonker, M. Green synthesis of nanoparticles and their biomedical applications: A review. *ACS Appl. Nano Mater.* **2021**, 4, 1142811-457.
44. Abebe, B.; Murthy, H.; Amare, E. Summary on Adsorption and Photocatalysis for Pollutant Remediation: Mini Review. *J. Encapsulation Adsorpt. Sci.* **2018**, 8, 225-255