


Version 2

<https://dx.doi.org/10.17504/protocols.io.4r3l29r6pv1y/v2>

¹Center of Excellence in Pharmaceutical Nanotechnology, Chiang Mai University, Chiang Mai

Mathurada Sasarom

Faculty of Pharmacy, Chiang Mai University



Edit and publish protocols, collaborate in communities, share insights through comments, and track progress with run records.

Create free account

DOI: <https://dx.doi.org/10.17504/protocols.io.4r3l29r6pv1y/v2>

Protocol Citation: Siriporn Okonogi, Mathurada Sasarom 2025. Biosynthesis of copper oxide nanoparticles with and without capping agents. **protocols.io** <https://dx.doi.org/10.17504/protocols.io.4r3l29r6pv1y/v2>Version created by **Mathurada Sasarom**

Manuscript citation:

Influence of capping agents on physicochemical properties and leukemic cytotoxicity of copper oxide nanoparticles biosynthesized using *Caesalpinia sappan* extract

License: This is an open access protocol distributed under the terms of the **Creative Commons Attribution License**, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited

Protocol status: Working

We use this protocol and it's working

Created: February 28, 2025

Last Modified: February 28, 2025

Protocol Integer ID: 123603

Keywords: metal nanoparticles, green synthesis, plant extract, biosynthesis of copper oxide nanoparticle, synthesis of copper oxide nanoparticle, copper oxide nanoparticle, reducing copper sulfate, copper sulfate, caesalpinia sappan

Funders Acknowledgements:

Thailand Research Fund through the Research and Researcher for Industry (RRI)

Grant ID: PHD59I0076

Abstract

This protocol describes the synthesis of copper oxide nanoparticles using a *Caesalpinia sappan* extract as a reducing agent with and without different capping agents. Copper oxide nanoparticles were prepared by reducing copper sulfate dissolved in water with the aqueousextract of *C. sappan* according to our previously described method (Sasarom et al, 2023).



Materials

Materials

1. Copper sulfate pentahydrate
2. Gelatin
3. Polyethylene glycol 400
4. Polysorbate 80
5. Octyl phenol ethoxylate
6. Sodium lauryl ether sulfate
7. Mannitol
8. Gelatin
9. Lyophilized powder of the extract of *C. sappan*
10. Ethanol
11. Sodium hydroxide
12. Milli-Q water

Equipment

1. Magnetic stirring
2. A centrifuge
3. a sonicator
4. An oven

Biosynthesis of copper oxide nanoparticles (CuONPs)

- 1 19 mL of 10 mM copper sulfate (or 44 mg per solution) were heated to 70°C for 10 min under magnetic stirring.
- 2 10 mL water, or 10 mL of studied capping agents (Gelatin, polyethylene glycol 400, polysorbate 80, octyl phenol ethoxylate, sodium lauryl ether sulfate and mannitol) was added to the copper solution.
- 3 60 mg of the lyophilized powder of the extract of *C. sappan* was dissolved in 6 mL water.
- 4 After 5 min of sonication, 1 mL of the extract was added to the different copper sulphate solutions which were subsequently stirred for 30 min at 70°C.
- 5 The acid mixtures (pH ~3) were adjusted to pH 10 by addition of 400 μ L of a 1 M NaOH solution and stirred for 2 h at 70°C.
- 6 The excess extract was removed by centrifugation of the nanoparticle dispersion at 8000 $\times$ g for 30 min.
- 7 The obtained pellet was redispersed in 30 mL milli-Q water and this precipitation/washing procedure was repeated two times.
- 8 The precipitate was dispersed in absolute ethanol and dried at 60°C for 8 h.
- 9 The particles were transferred into light-protecting containers and stored in a desiccator at room temperature until use.

Protocol references

Sasarom M, Wanachantararak P, Chaijareenont P, Okonogi S. Biosynthesis of copper oxide nanoparticles using *Caesalpinia sappan* extract: *In vitro* evaluation of antifungal and antibiofilm activities against *Candida albicans*. 2023;17(4):238–247.